Marked up Version of the Claims

- 1. CANCELLED
- 2. CANCELLED
- 3. CANCELLED
- 4. CANCELLED
- 5. CANCELLED
- 6. CANCELLED
- 7. CANCELLED
- 8. CANCELLED
- 9. CANCELLED
- 10. (Previously Presented) An element for the casting of a liquid metal, comprising a base body made from a refractory material, said body comprising an outer surface and an inner surface defining a pouring channel for the casting of the liquid metal, wherein at least a part of the element inner surface is coated with an insulating coating comprising insulating hollow microspheres, preferably in an amount comprised between 5 and 40 weight % and forming, at the metal liquid contact, a gas impermeable layer.
- 11. (Currently Amended) A casting element according to claim [1]10, wherein the coating comprises 20 to 80 weight % of a ceramic matrix.
- 12. (Previously Presented) A casting element according to claim 11, wherein the ceramic matrix comprises silica or alumina.
- 13. (Currently Amended) A casting element according to claim [2]12, wherein the ceramic matrix comprises vitreous grains.
- 14. (Previously Presented) A casting element according to claim 13, wherein the vitreous grains comprise atomized silica.

- 15. (Currently Amended) A casting element according to claim [1]10, wherein the thickness of the coating is between 1 and 10 mm.
- 16. (Currently Amended) A casting element according to claim [1]10, wherein the impermeable layer and the refractory material are interpenetrated.
- 17. (Currently Amended) A casting element according to claim [1]10, wherein the base body is constituted from a carbon bonded material.
- 18. (Currently Amended) A casting element according to claim [1]10, wherein the casting element is a pouring shroud.
- 19. (Currently Amended) A casting element according to claim [1]10, wherein at least a part of the external surface is coated with an insulating coating comprising insulating microspheres.
- 20. (Previously Presented) A casting element according to claim 19, wherein the insulating microspheres comprise between 5 and 40 weight % of the insulating coating.
- 21. (Previously Presented) A method of coating a casting element comprising a base body made from a refractory material, said body comprising an outer surface and an inner surface defining a pouring channel for the casting of the liquid metal, comprising the steps of preparing a slip comprising insulating hollow microspheres, drying the slip at room temperature, preferably for at least two hours, and forming a gas impermeable layer from the dried slip by contacting the dried slip with liquid metal.